



Date of Publication: April 23, 2010

### Technical Data Sheet: ACAOUVIA

Item Number: ACAOUVI

Item Name: Hindered Amine Light Stabilizer/UV Absorber/Antioxidant Concentrate

Let Down Resin: PP and PE

Regulatory Status:  Heavy Metal Free  CONEG  
 RoHS  WEE Compliant  
 Not Radioactive  FDA – Indirect Food Contact\*  
 No REACH Substances of Very High Concern

Processing Range 190°C - 220°C Do not exceed 260°C  
Melting Range 120°C - 175°C

Let Down Ratio: \*As required\*

#### Guidelines for use:

ACAOUVI is designed to improve the weather stability of the resin for your end application. ACAOUVI contains 12.5% HALS, 6% UV absorber and 1% antioxidant. Match the usage rate with the desired end application performance. After the usage rate has been determined, final application testing is recommended to ensure part performance is in accordance with all applicable specifications.

**Disclaimer:** The data contained in this report is being provided by Uniform Color Company ("UCC") as a complimentary service, and as such, is being provided without warranty (express or implied) or representation as to its accuracy or completeness. Moreover, this report is intended only for the internal use of the recipient, and shall not be disclosed to any third party, nor reproduced or distributed by the recipient, without UCC's prior written consent. The end user is solely responsible for the physical property requirements of their end application. UCC recommends that the end user performs all relevant physical testing to ensure no adverse results from the use of this product are experienced.

942 Brooks Avenue Holland MI 49423

(616) 394.3800 · (800) 44.COLOR

Fax: (616) 394.3824

[uniformcolor.com](http://uniformcolor.com)