



Date of Publication: April 23, 2010

Technical Data Sheet: ACSLIP

Item Number: ACSLIP

Item Name: Polyethylene Slip Concentrate

Let Down Resin: Polyolefins and TPOs

Regulatory Status: Heavy Metal Free CONEG
 RoHS WEE Compliant
 Not Radioactive FDA – Indirect Food Contact*
 No REACH Substances of Very High Concern

Processing Range 200°C - 240 °C Do not exceed 260°C
Melting Point 110°C

Let Down Ratio: *As required*

Guidelines for use:

Begin adding ACSLIP at a usage rate of 1% and increase usage until reaching the desired slip performance. After the usage rate has been determined, final application testing is recommended to ensure part performance is in accordance with all applicable specifications. ACSLIP is best suited for LDPE applications but is compatible with all polyolefins and TPO's.

*Call UCC for details on FDA limitations of use.

Disclaimer: The data contained in this report is being provided by Uniform Color Company ("UCC") as a complimentary service, and as such, is being provided without warranty (express or implied) or representation as to its accuracy or completeness. Moreover, this report is intended only for the internal use of the recipient, and shall not be disclosed to any third party, nor reproduced or distributed by the recipient, without UCC's prior

942 Brooks Avenue Holland MI 49423

(616) 394.3800 · (800) 44.COLOR

Fax: (616) 394.3824

uniformcolor.com



written consent. The end user is solely responsible for the physical property requirements of their end application. UCC recommends that the end user performs all relevant physical testing to ensure no adverse results from the use of this product are experienced.

942 Brooks Avenue Holland MI 49423

(616) 394.3800 · (800) 44.COLOR

Fax: (616) 394.3824

uniformcolor.com